

AEROSOL[®] NPES 930P

surfactant

Type:	Anionic
Chemical:	Ammonium Salt of Sulfated Nonylphenoxypoly (Ethyleneoxy) Ethanol
CAS No:	9051-57-4
Molecular Formula:	$C_{33}H_{63}NO_{13}S$
Molecular Weight:	713
EPA Status:	Exempt 40 CFR 180.1001 (d)
FDA Status:	Approved 21 CFR 175.105, 176.180

The versatile AEROSOL NPES 930P surfactant can be effectively used as the sole emulsifier in the preparation of a wide variety of latexes—

- Acrylic Latex
- Vinyl Acetate Latex
- Vinyl Acetate/Acrylic Latex
- Styrene/Acrylic Latex
- Zinc-Crosslinking Floor Finish Latex

Latex systems produced with low usage levels of AEROSOL NPES 930P surfactant exhibit the following properties:

- Extremely low levels of coagulum
- Fine particle size
- Excellent mechanical stability
- Cation tolerance
- Excellent freeze-thaw stability
- Superior properties in latex films
 - High optical clarity
 - Uniformity in appearance
 - Improved water-spot resistance

PHYSICAL AND CHEMICAL PROPERTIES

Appearance at 25°C (77°F)	Clear, yellow liquid
Active solids, % by weight (MW = 713)	30.0-32.0
Moisture, % by weight, maximum	70
pH (10% Solution)	7.0-7.5
Color, APHA, as is, maximum	150
Iron, ppm, maximum	5
Specific gravity, 25°C	~1.04
Density, lb/gal, 25°C	~8.7
Viscosity, cps, 25°C	~90
Flash point, °F	>200
Gel point, °F	<55 (12.8°C)

SOLUBILITY

In polar organic solvents	Insoluble
In nonpolar organic solvents	Insoluble
In water	Complete

ELECTROLYTE TOLERANCE

Calcium Tolerance

AEROSOL NPES 930P surfactant	Calcium tolerance
<u>Concentration, % solids</u>	<u>ppm</u>
0.50	>2250

CYTEC

CYTEC INDUSTRIES INC.

Process Chemicals
Five Garret Mountain Plaza
West Paterson, NJ 07424-3360
973-357-3100
800-253-4078
<http://www.cytec.com>

PRT-716-B

SURFACE ACTIVE PROPERTIES

Critical Micelle Concentration (CMC), % by weight	0.016-0.030		
Surface Tension at CMC, dynes/cm	39.5		
Ross Miles Foam Test, ASTM D-1173, 0.5% solution, 25°C			
Initial foam volume, mL	270		
Foam Volume after 15 minutes, mL	125		
Wetting (Draves Test)			
Draves Sinking Time in seconds at 25±1°C			
% Concentration	1.0	0.5	0.1
Time in seconds	55.2	73	199.5

EPA STATUS¹

Under the provisions of 40 CFR 180.1001 (d) of the Pesticides Chemicals Regulations, AEROSOL NPES 930P surfactant is exempted from the requirements of a tolerance when used in accordance with good agricultural practice as an inert ingredient of pesticide formulations applied to growing crops.

¹ 21 CFR 182.99 Adjuvants for Pesticide Chemicals—Adjuvants, identified and used in accordance with 40 CFR 180.1001 (c) and (d), which are added to pesticide use dilutions by a grower or applicator prior to application to the raw agricultural commodity, are exempt from the requirement of tolerance.

FDA STATUS

AEROSOL NPES 930P surfactant is permitted for use under Sections:

21 CFR 175.105 Adhesives. No limitations other than the general limitations given in Section 174.5.
21 CFR 176.180 Components of paper and paper board in contact with dry food. No limitations other than the general limitations given in Section 174.5.

HEALTH AND SAFETY INFORMATION

Before handling this material, read the corresponding Cytec Industries Inc. Material Safety Data Sheet for safety, health and environmental data.

The acute oral (rat) LD₅₀ for this product is greater than 10 g/kg. Direct dermal contact with the liquid may cause severe irritation including swelling, itching and painful burning. Direct eye contact with the liquid may cause severe irritation including inflammation of the outer eye and painful burning. Inhalation or overexposure to the mist may cause irritation of the eyes, nose and throat.

STORAGE AND HANDLING

Solutions of AEROSOL NPES 930P may be stored and used in a wide variety of containers or reaction vessels. Stainless steel, aluminum and Monel are recommended for reaction and storage vessels; glass and rubber are suitable lining materials. Some of the sprayed resinous coatings are satisfactory in stationary tanks in which the coating can be built up more heavily than is customary in drums. In permanent installations, however, the added expense of aluminum, stainless steel or clad-steel frequently is justified.

The efficacy of AEROSOL NPES 930P surfactant is not impaired by freezing and thawing. However, if a freeze-thaw occurs, it is recommended that the entire contents of the container be agitated prior to use.

IMPORTANT NOTICE

The information and statements herein are believed to be reliable but are not to be construed as a warranty or representation for which we assume legal responsibility. Users should undertake sufficient verification and testing to determine the suitability for their own particular purpose of any information or products referred to herein. NO WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE IS MADE. Nothing herein is to be taken as permission, inducement or recommendation to practice any patented invention without a license.

TRADEMARK NOTICE

The ® indicates a Registered Trademark in the United States and the ™ or * indicates a Trademark in the United States. The mark may also be registered, the subject of an application for registration or a trademark in other countries.

TSCA INFORMATION

This product is manufactured in compliance with all provisions of the Toxic Substances Control Act, 15 U.S.C.

CYTEC

- **Asia/Pacific** - Cytec Industries Pte. Ltd., Singapore, tel. 65-733-6788, fax. 65-735-7783
- **Europe** - Cytec Industries B.V., Botlek, the Netherlands, tel. 31-181-295400, fax. 31-181-295401
- **Latin America** - Cytec de Argentina S.A., Buenos Aires, tel. 541-331-5088, fax. 541-345-7947
- **United States** - Cytec Industries Inc., West Paterson, NJ, U.S.A., tel. 973-357-3100, fax. 973-357-3055